

⑫

EUROPEAN PATENT APPLICATION

⑰ Application number: 83302903.6

⑤① Int. Cl.³: **A 61 L 15/00**

⑱ Date of filing: 20.05.83

⑲ Priority: 21.05.82 US 380646

⑦① Applicant: **PERSONAL PRODUCTS COMPANY**, Van Liew Avenue, Milltown New Jersey 08850 (US)

⑳ Date of publication of application: 28.12.83
Bulletin 83/52


⑦② Inventor: **Korpman, Ralf**, 885 Bluestone Lane, Bridgewater New Jersey 08807 (US)

㉑ Designated Contracting States: AT BE CH DE FR IT LI NL SE

⑦③ Representative: **Jones, Alan John et al, CARPMAELS & RANSFORD** 43 Bloomsbury Square, London, WC1A 2RA (GB)

㉒ Absorbent panel suitable for use in absorbent products and process for its production.

㉓ The invention provides an absorbent panel which consists of a paper, film or fabric substrate coated on at least one surface with a reactive composition containing from 10 to 40 parts by weight of a liquid polyhydroxy organic compound and from 90 to 60 parts by weight of a particulate water-insoluble, water-swellaible absorbent polymer having a gel capacity of at least 10. The absorbent panel is capable of absorbing at least 15 times its weight of liquid and is a thin structure.



EP 0 096 976 A2

ABSORBENT PANEL SUITABLE FOR USE IN ABSORBENT PRODUCTS
AND PROCESS FOR ITS PRODUCTION

Background of the Invention

5 The present invention relates to an absorbent panel which is suitable for use in absorbent products such as incontinence pads, disposable diapers, sanitary napkins, tampons and the like. More particularly, the absorbent panel utilizes a superabsorbent composition.

10 Disposable absorbent products for body fluids are commonplace in today's market. These products include incontinence pads, disposable diapers, sanitary napkins, tampons, adult incontinence systems and the like. Generally, in

15 each of these products a fibrous batt is included which holds the liquid. These fibrous batts, although somewhat efficient, do not hold sufficient liquid or leak so as to cause a problem for the user. Superabsorbents, otherwise identified as hydrogels or hydrocolloids, have been

20 incorporated in the fibrous batt structures and used in the articles mentioned above to increase their absorptive efficiency. The expected advantage of incorporating these materials which are in particulate form, is diminished by the shifting of the particulate materials in the articles

25 during shipment and use by the wearer. Furthermore, the fibrous batts tend to be bulky and can provide discomfort to the wearer. A means of decreasing the mobility of the particulate absorbent materials and providing a structure which is not so bulky is desirable. U.S. Patent No.

30 3,900,030 to Bashan describes a catamenial tampon which utilizes an open-celled polymer foam which has the water-swellaable polymers imbedded therein. While this provides structural integrity to the absorbent polymer, versatility in application is governed by the foam carrier. Moreover,

35 the method of disposition is dictated by the foam carrier.

Summary of the Present Invention

The present invention provides an absorbent panel which consists of a paper, film or fabric substrate coated on at least one surface with a reactive composition. The reactive composition contains from about 10 to about 40 parts by weight of a liquid polyhydroxy organic compound and from about 90 to about 60 parts by weight of a particulate water-insoluble, water-swellaible absorbent polymer having a gel capacity of at least 10. Such an absorbent panel is capable of absorbing at least 15 times its weight of liquid or body fluid and yet is a relatively thin structure. The present invention also provides a method for making the absorbent panel and articles utilizing the absorbent panel.

Brief Description of the Drawings

Figure 1 is a schematic drawing of a method of manufacture of the absorbent panel of the present invention.

Figure 2 is an enlarged portion from Figure 1 illustrating a fraction of the absorbent panel of the present invention.

Figure 3 is a perspective view of a disposable diaper with a portion broken away for clarity illustrating one embodiment of the present invention.

Figure 4 is a perspective drawing of a sanitary napkin illustrating one embodiment of the present invention.

Figure 5 is a cross-section view, along lines 5-5 of Figure 4.

Figure 6 is a perspective view of a blank for a tampon illustrating one embodiment of the present invention.

Figure 7 is a perspective view of a tampon with a portion
5 broken away for illustrative purposes.

Detailed Description of the Invention

10 In accordance with the present invention, an absorbent panel is provided which comprises a paper, film, or fabric substrate coated on at least one surface with a reactive composition. The substrate coated with the reactive
15 composition provides a relatively thin absorbent panel which can be used as supplementary to a fibrous batt in an absorbent product or in place of a fibrous batt in an absorbent product.

The reactive composition contains from about 10 to about 40 parts by weight of a liquid polyhydroxy organic
20 compound and from about 90 to about 60 parts by weight of a particulate water-insoluble, water-swellable absorbent polymer having a gel capacity of at least 10.

25 The liquid polyhydroxy organic compound employed in the present invention is a liquid with a high boiling point having at least two hydroxy groups preferably vicinal or adjacent hydroxy groups. Suitable liquids include glycerol, ethylene glycol, propylene glycol and the like. Glycerol and ethylene glycol are preferred.

30 The water-insoluble, water-swellable absorbent polymer is generally a lightly cross-linked polymer containing a plurality of hydrophilic groups such as carboxyl, carboxamide, sulfonate salt or hydroxyl groups along the
35 polymer chain in insufficient proportions so that the polymer would be water-soluble if it were not for the

cross-linking thereof. In these polymers the hydrophilic groups constitute at least 25 percent and up to 72 percent of their molecular structure. The materials are of sufficient molecular weight or degree of cross-linking to
5 be water-insoluble while water-swellaable. Many of the materials are those which have been reported to have an average molecular weight per cross-linkage in the range of from about 13,000 to about 300,000 but are not limited thereto. The most common and best known of such materials
10 are polyacrylates, modified polysaccharides, cross-linked synthetic polyacrylates, cross-linked carboxymethylcelluloses, or cross-linked poly(alkyleneoxide)s as hereinafter defined. Other graft polymers of polysaccharides and natural gums such as xanthan gum, locust gum, guar gum and
15 the like or blends thereof are also suitable provided they meet the requirements of water-insolubility and water-swellaability. The water-insoluble, water-swellaable polymers have a gel capacity of at least about 10. By "gel capacity" is meant the weight of aqueous fluid which
20 can be imbibed and held per unit weight of polymer, i.e., grams of fluid per gram of polymer. Stated another way, the absorbent polymers have an absorbent capacity of at least 10 times the weight of the material in dry form. Commonly it is about 15 to 70 times the dry weight. The
25 materials are frequently spoken of in the art as hydrogels, hydrocolloids, or superabsorbents. Many of the water-swellaable polymers are available commercially.

The polymers are provided in particulate form. By
30 "particulate" is meant a substance in the form of fine discrete particles. The particles may vary in shape such as spherical, rounded, angular, acicular, irregular, or fibrous. The particles generally range in size from about 1 micron to 2×10^4 microns in diameter or a cross-section
35 (largest dimension when not spherical). The particles are

preferably of finely divided powder of particle size from about 1 to about 10^3 microns.

Referring now to the drawings, Figure 1 schematically illustrates a method for preparing the absorbent panel of the present invention. In Figure 1 a substrate 11, either paper, film, or fabric, is provided by a roll 10. The substrate 11 is conveyed by a conveyor 12 along a predetermined path. The liquid polyhydroxy organic compound 14 is sprayed by a spraying mechanism 13 onto one side of the substrate 11. The absorbent polymer 16 in powder form is applied in a substantially even layer with the desired amount on top of the liquid organic compound. More of the liquid polyhydroxy organic compound 14 is applied by a sprayer 17 on top of the powdered absorbent polymer. The reactive composition which has formed on the substrate is then subjected to heat, if desired, by a heat unit 18 which raises the temperature of the reactive mixture to between 93 and 205°C (200 and 400°F) to allow the reactive composition to fuse. The substrate containing the coating, thus forming the absorbent panel of the present invention, is then rolled on a roll 19 for storage until the desired time of use. The absorbent panel in the form of a strip may be cut into the desired shapes and sizes for its subsequent use.

Referring now to Figure 2, a fragment of the absorbent panel is shown. This fragment 20 consists of the substrate 22, a layer of liquid polyhydroxy organic compound 24, a layer of absorbent polymer 26 and a final layer of liquid polyhydroxy organic compound 23. Reaction has taken place between the organic compound and the absorbent polymer which reaction in this particular instance has been fused by heat, however, heat is used only to speed the fusion. The resulting layers have formed a film on the substrate which film is flexible and permanently

affixed to the substrate. Thus the absorbent polymer is securely fixed in position on the absorbent panel.

5 In Figure 3 a perspective view is shown of a disposable
diaper 30 with a portion broken away for clarity. A
moisture impermeable backing 32 is provided
upon which is placed an absorbent panel 34. The absorbent
core is an absorbent panel of the present invention. The
upper surface of the diaper consists of a facing sheet 36
10 which is moisture-permeable. The facing sheet and backing
sheet are held together in the margin by glue lines 37.
These glue lines also assist in maintaining the position
of the absorbent panel in the diaper structure. Tape tabs
38 are provided for securing the diaper about the wearer.

15 Figure 4 illustrates a sanitary napkin 40 having a cover
wrap 42. Figure 5 is a cross-sectional view along lines
5-5 of the sanitary napkin illustrated in Figure 4. The
cover wrap 42 is generally a moisture-permeable nonwoven
20 fabric. The absorbent core 53 in this instance consists
of a fibrous absorbent batt 54 and an absorbent panel 56
of the present invention. A moisture-impermeable barrier
sheet 58 is provided to prevent leakage when the absorbent
core becomes somewhat saturated.


25 Figure 6 provides a tampon blank 60, which when rolled and
placed in a tampon forming process, produces a tampon 70 as
as appears in Figure 7. The blank 60 is provided with an
absorbent batt layer 62 and an absorbent panel 64 of the
30 present invention. These layers are merely placed
adjacent one another and rolled as illustrated. In Figure
7 the fibrous batt 72 and the absorbent panel 74 appear
adjacent one another in roll form as illustrated in the
broken away portion of the figure.

Many water-insoluble, water-swellaable polymers suitable as absorbent are available commercially. They also may be prepared by cross-linking a pre-formed water-soluble, straight chain polymer, by polymerizing an appropriate monomer or a monomer with a co-monomer to effect simultaneous polymerization and cross-linking, or by incorporating a hydrophilic group into a completed polymer. An example of a later incorporation of a hydrophilic group to the completed polymer is the incorporation by sulfonation of a sulfonic acid moiety. When it is desired to have the hydrophilic group in the salt form, the polymer may be prepared first as an acid, ester, amide, or nitrile and the product hydrolyzed in whole or in part.

The preferred polymers have an acrylate group in their molecular structure. They may be completely synthetic acrylate polymers or acrylate modified polysaccharides, e.g., acrylate modified starch or acrylate modified cellulose. By "acrylate modified" is meant that an acrylate polymer or polyacrylate as hereinafter described has been grafted onto the polysaccharide. "Acrylate polymer" or "polyacrylate" as herein employed embraces not only polymers which contain acrylate salt groups but those which also may contain an acrylamide, acrylic acid, acrylic ester group or acrylonitrile group.

The preferred synthetic acrylate polymer absorbents are those which have a salt group, an acid group, or which have both an amide group and a salt or acid group. These have been represented in the literature, e.g., U.S. Patent 3,686,024, by the following formula:

5



10 where A is an alkali metal ion such as sodium or potassium, or is hydrogen, n is from about 0.5 to about 0.9, 1-n defines the extent of hydrolysis, and z is the number of mer units between cross-links.


15 The polyacrylate absorbent containing both amide and carboxylate groups may be prepared either (1) by aqueous polymerization of acrylamide with a difunctional organic cross-linker such as N,N'-methylenebisacrylamide in the presence of a free radical catalyst to obtain a water-swellingable, cross-linked polyacrylamide, followed by
20 partial hydrolysis in aqueous alkali to obtain a cross-linked polymer having both an amide and an alkali metal carboxylate groups as more fully described in U.S. Patent 3,247,171, or (2) by copolymerization of acrylamide and
25 acrylic acid alkali metal salt in the presence of a cross-linking monomer such as N,N'-methylenebisacrylamide and a catalyst system such as 1:1 ammonium persulfate and β-dimethyl-aminopropionitrile, also described in the aforesaid patent, or (3) by radiation polymerization and
30 cross-linking as described in U.S. 4,192,727.

Polyacrylate absorbents also may be prepared by subjecting linear polyacrylate to high energy radiation cross-linking as described in U.S. Patent 3,229,769, or to chemical
35 polymerization and cross-linking, as described in British

Patent 719,330, or may be prepared by cross-linking of a previously prepared polyacrylamide.

Acrylate modified polysaccharides are those which have a polyacrylate chain grafted onto a cellulose or starch molecule. They are preferred graft copolymers of polysaccharides which have hydrophilic chains grafted thereon. By "hydrophilic chain" is meant a polymer chain obtained from monomers which have a group which is water-soluble or becomes water-soluble on hydrolysis, e.g., carboxyl, sulfonic, hydroxyl, amide, amino, quaternary ammonium and hydrolysis products thereof. In the polysaccharides acrylate polymers, a hydrophilic chain of the general formula

15



is attached to the backbone of the cellulose or starch molecule through a carbon linkage. In the formula,

$\begin{array}{c} \text{O} \\ || \\ \text{---C-A} \end{array}$ and $\begin{array}{c} \text{O} \\ || \\ \text{---C-B} \end{array}$ independently represents an acid, ester, alkali metal, ammonium salt or amide group, each R independently is hydrogen or lower alkyl, r is an integer of from 0 to about 5,000 and s is an integer of from 0 to about 5,000, and r+s is at least 500.

The polysaccharide acrylate polymers may be prepared employing well known procedures for carrying out graft

copolymerization of olefinically unsaturated chains onto cellulose and starch in which grafting of the hydrophilic material onto a starch or cellulose backbone is accomplished simultaneously with the formation of the hydrophilic polymeric material, and, if necessary, followed by hydrolysis. Thus, the polymers may be prepared by the polymerization of an appropriate polysaccharide with an appropriate acrylic monomer such as acrylonitrile, methacrylonitrile, methyl or ethyl acrylate, acrylic or methacrylic acid, or with acrylamide or methacrylamide, followed by alkaline hydrolysis or by the polymerization of alkali metal salt of acrylic or methacrylic acid with the appropriate polysaccharide.

The polymerization is carried out in the presence of a free radical catalyst system in an aqueous medium, or by irradiation (ultra-violet, gamma-, or X-radiation). Catalyst systems for employment in aqueous media usually comprise an inorganic oxidizing agent as initiator and an inorganic reducing agent as activator. Representative oxidizing agent initiators are inorganic persulfates, peroxides and alkali metal bromates and chlorates. Representative reducing agent activators are alkali metal bisulfites, sulfites, ferrous ammonium sulfate, and alkali metal thiosulfate.

In a method for carrying out graft polymerization employing a catalyst system, the inorganic oxidizing agent initiator and the inorganic reducing agent activator each as an aqueous solution are alternately added to a reaction medium comprising a water-solution of an acrylate monomer, a co-monomer, a cross-linking monomer, and a dispersion of pulverulent or fibrous water-insoluble, water-swella-ble polysaccharide in water-immiscible organic liquid containing a minor amount of water-miscible solvent to obtain an acrylate modified polysaccharide product as more fully

described in U.S. Patent 4,028,290. Other suitable methods for chemical catalytic graft polymerization may be found in U.S. Patent 3,256,372; 3,661,815; 4,076,663; 3,889,678 and 4,105,033.

5

Suitable polysaccharide acrylate polymers are those in which the hydrophilic chain loading on the backbone is in the range of from about 10 percent by weight to about 90 percent by weight, usually from about 40 to 80 percent by weight of the polysaccharide acrylate polymer.

10

Other suitable water-insoluble, water-swellaable polymers include cross-linked carboxymethylcellulose (CMC) obtained as described, for example, in U.S. Patent 2,639,239, cross-linked poly(alkylene oxide) of molecular weight of at least 100,000, obtained as described, for example, in U.S. Patent 3,956,224; 3,264,202; 3,957,605 and 3,898,143; and blends of organic substances of polysaccharide character, e.g., natural or synthetic gums. It has been found generally that when gums are employed they must be employed as blends. It appears that the polysaccharide gums which are normally soluble interact when employed as blends to have the desirable swellability without the undesirable solubility. Typical gums which may be employed in blends include locust bean gum, guar gum, xantham gum, tragacanth gum, karaya gum and the like. Gum blends as well as the absorbent polymers above described are available commercially under various trade names.

20

25

30

35

The water-insoluble, water-swellaable polymers prepared by any of the foregoing methods are generally obtained as stiff, brittle solids. These may be comminuted to the appropriate size. Preferably they are employed in the form of powder as previously defined, but may also be employed in other forms.

The liquid polyhydroxy compounds which are suitable from the currently available hydroxy compounds are quite limited and are substantially as previously defined. To reiterate these polyhydroxy organic compounds have a high boiling point and generally include glycerol, ethylene glycol, propylene glycol and the like.

The reactive composition formed by the combination of the liquid polyhydroxy organic compound and the absorbent polymer is formed in a number of ways. Previously illustrated is the method of spraying the liquid onto a substrate and spreading the polymer in powder form followed by another liquid layer on top of the powder. This is sufficient contact to permit the reactive composition to react and adhere to the substrate so as to form the absorbent panel. When applying the components stepwise it is not required to place a liquid layer on the substrate first. In other words, that step may be eliminated and the procedure would simply be spreading the powder onto the substrate and then spraying a liquid layer over the powder.

As mentioned heretofore, the substrate may be either paper, film, or fabric. It is preferred that a paper substrate be a relatively soft flexible receptive substrate. In other words, a high polished slick paper would not be as suitable because of its stiffness and it would not be as receptive to the reactive composition as a softer, more porous paper. An example of a suitable paper substrate is tissue. The film substrate may be any known film, preferably one with integrity and flexibility. The fabric substrate may be a woven textile or a nonwoven fabric such as a polyester, polypropylene or polyethylene fabric. It is preferred that the fabric be moisture permeable so that the entire substrate is utilized as a part of the absorbent panel. The amount of the reactive mixture

applied to the substrate will vary according to the absorption required in the ultimate environment. It may be desirous to make the reactive composition layer sufficiently thin so as to prevent gel blocking when the absorbent polymer is receiving liquid. By "gel blocking" is meant particles of absorbent polymer sufficiently close that when they swell they make contact with one another and form a substantially continuous layer of a gel which would be impervious to subsequent liquid or moisture. In some instances of use, it may not be necessary for gel blocking to be avoided and consequently a relatively large amount of the reactive composition can be applied to the substrate.

For forming the absorbent panels mentioned above used in diapers, sanitary napkins, tampons and the like, it is recommended that the reactive mixture be applied in an amount ranging from about 10 to about 250 gm/square meter.

The following examples are illustrative of the present invention.

Examples 1 - 5

Reaction compositions were prepared on tissue substrate according to the formulations shown in Table I below. All parts are in parts by weight.

Table I

	COMPONENTS	EXAMPLES				
		1	2	3	4	5
5		(Parts by Weight)				
	Glycerol				15	25
	Ethylene Glycol	15	25	10		
10	Permasorb 20 (cross-linked ionic polyacrylate, National Starch)	85				
15	Sanyo 300 (polyacrylate, Sanyo)		75		85	
20	Henkel 147 (starch polyacrylate, Henkel)			90		75

25 Approximately one-half of the polyhydroxy organic compound was sprayed onto the tissue substrate. The absorbent polymer was then sprinkled evenly on the organic compound and the remaining organic compound was sprayed on top of the absorbent polymer. The resulting reaction composition was subjected to a temperature of 93°C (200°F.) for about 10

30 seconds to enhance fusion of the reaction composition.

35 The foregoing description and the drawings are illustrative and are not to be taken as limiting. Still other variations and modifications are possible without departing from the spirit and scope of the present invention.

Claim(s) Nr 18+19
to be abandoned

0096976

IN THE CLAIMS:

1. An absorbent panel comprising a paper, film or fabric substrate coated on at least one surface thereof with a reactive composition of from about 10 to about 5 40 parts by weight of a liquid polyhydroxy organic compound and the from about 90 to about 60 parts by weight of a particulate water-insoluble, water-swellable absorbent polymer having a gel capacity of at least 10.
2. The absorbent panel of claim 1 wherein the 10 liquid polyhydroxy organic compound is selected from the group consisting of glycerol, ethylene glycol and propylene glycol.
3. The absorbent panel of claim 1 or claim 2 wherein the absorbent polymer is a polyacrylate.
- 15 4. The absorbent panel of any one of claims 1 to 3 wherein the substrate is paper.
5. The absorbent panel of any one of claims 1 to 3 wherein the substrate is a fabric.
- 20 6. The absorbent panel of claim 5 wherein the fabric is a nonwoven fabric.
7. The absorbent panel of claim 6 wherein the nonwoven fabric is polyester.
8. The absorbent panel of any one of claims 1 to 7 wherein the reactive composition comprises from about 25 20 to about 30 parts of the organic compound and from about 80 to about 70 parts of the absorbent polymer.
9. A disposable absorbent structure containing an absorbent core comprising an absorbent panel 30 according to any one of claims 1 to 8.
10. The absorbent structure of claim 9 and including a lightly compacted cellulosic fibrous batt in juxtaposition with said absorbent panel.
11. A disposable diaper having a moisture-impermeable 35 backing, an absorbent core comprising an absorbent panel according to any one of claims 1 to 8, and a moisture permeable facing sheet, said absorbent core being sandwiched between said facing sheet and said backing sheet.

12. A sanitary napkin containing an absorbent core comprising an absorbent panel according to any one of claims 1 to 8.

13. The sanitary napkin of claim 12 wherein the absorbent core further comprises a loosely-compacted, cellulosic, fibrous batt placed in juxtaposition with said absorbent panel.

14. The sanitary napkin of claim 12 or claim 13 wherein the absorbent core comprises said absorbent panel surrounded by a loosely-compacted cellulosic fibrous batt.

15. A tampon containing an absorbent core comprising an absorbent panel according to any one of claims 1 to 8.

16. A process for preparing an absorbent panel comprising:

(a) providing a paper, film, or fabric substrate with a thin layer of a particulate water-insoluble, water-swellaible absorbent polymer having a gel capacity of at least 10;

(b) coating the substrate on the side of the layer of particulate polymer with a liquid polyhydroxy organic compound to provide a reactive composition on the substrate, the composition containing from about 10 to about 40 parts by weight of said organic compound and from about 90 to about 60 parts by weight of said particulate polymer; and




(c) fusing said reactive composition.

17. The process of claim 16 wherein said reactive composition is present on said substrate in an amount from about 10 to about 250 grams per square meter.

18. An absorbent panel, substantially as hereinbefore described with reference to the accompanying drawings.

19. A process for producing an absorbent panel, substantially as hereinbefore described with reference to the accompanying drawings.

1/2



2/2

